

Plastic Belly Cap Chemical Compatibility

CHEMICAL	R/X
Acetamide, 50%	R
Aluminum Salts	R
Alums	X
Ammonium Chloride, 10%	R
Ammonium Salts	X
Aniline	X
Aniseed Oil	R
Antifreeze Compounds	R
Aqua Regia	X
Attar Of Roses	R
Barium Salts	R
Benzoic Acid	X
Benzole	R
Borax (Sodium Tetraborate)	R
Boric Acid	X
Brake Fluid	R
Butylene Glycol	X
Butyric Acid	X
Calcium Chloride, 10%	R
Camphor	R
Carbon Disulfide	R
Carbon Tetrachloride	R
Catechol, 6%	X
Caustic Soda, 40%	R
Chlorinated Lime	X
Chloroacetic Acid	X
Chlorobromomethane	X
Chloroform	X
Chrome Baths	X
Chromic Acid	X
Chromium Salts	R
Copper Salts, 10%	R
Cresol	X
Decalin	R
Dibutyl Phthalate	R
Dimethyl Formamide	X
Diocetyl Phthalate	R
Ethylene Chloride	X

CHEMICAL	R/X
Formaldehyde, 40%	X
Formalin	X
Formamide	X
Formic Acid	X
Freon	R
Furfurol	X
Glycerine	R
Glycol	R
Heptyl Acetate	R
Hydraulic Fluid	R
Hydrochloric Acid	X
Hydrogen Fluoride, 40%	X
Hydrogen Peroxide	X
Iron Salts (Acidic Solution), 20%	X
Iron Salts (Neutral Solution), 20%	R
Lactic Acid	X
Lead Salts	R
Linseed Oil	R
Magnesium Hydroxide, 10%	R
Magnesium Salts, 10%	R
Mercury	R
Mercury Salts (Neutral Solution)	R
Methylene Chloride	X
Mineral Oils	R
Neodecanoic Acid	X
Nickel Salts	R
Nitric Acid	X
Nitrobenzene	X
Oleic Acid	R
Oleum	X
Oxalic Acid, 10%	X
Perchloroethylene	R
Phenol	X
Phosphoric Acid	X
Plasticizers (Phthalates, Phosphates)	R
Potassium Bromide, 10%	R
Potassium Chlorate, 5-7%	X
Potassium Hydroxide, 50%	R

R = Resistant with little to no chemical attack.

X = Not resistant due to moderate to severe chemical attack.

All statements, data, and information contained herein are believed to be accurate and reliable but are presented without guarantee, warranty, or responsibility of any kind, expressed or implied. You expressly understand and agree that Salco Products assumes NO obligation or liability for the statements, data, and information given. Further, you expressly understand and agree that all results which may be obtained from any use of this document are to be accepted by you at your risk alone. Salco Products hereby DISCLAIMS ALL liability for any use of this document.

You must evaluate and determine whether a material is suitable for your intended application. We recommend that you perform tests to determine the propriety of a material for your particular purpose prior to use.

In NO case shall anything contained in this document be considered a part of our terms and conditions of sale.

Statements or suggestions concerning the possible use of any material are made WITHOUT representation of warranty that any such use is free of patent infringement. We do NOT recommend that any patent be infringed. The user should NOT assume that all safety measures are indicated or that other measures may not be required.

Revised 5/14/07

Plastic Belly Cap Chemical Compatibility

CHEMICAL	R/X
Potassium Iodide, 10%	R
Potassium Nitrate, 10%	R
Potassium Permanganate, 1%	X
Potassium Sulfate, 10%	R
Resorcinol	X
Salicylic Acid	R
Silicone Oils	R
Silver Salts	R
Sodium Bicarbonate	R
Sodium Bisulphite, 10%	R
Sodium Bromide, 10%	X
Sodium Carbonate, 10%	R
Sodium Chloride	R
Sodium Chlorite, 5%	X
Sodium Hydroxide, 40%	R
Sodium Hypochlorite, 5%	X
Sodium Nitrate, 10%	R
Sodium Nitrite, 5%	X
Sodium Perborate, 5%	X
Sodium Phosphate, 10%	R
Sodium Sulfate, 10%	R
Sodium Sulfide, 10%	R
Sodium Sulfite, 10%	R
Sodium Thiosulfite	R
Soya Oil	R
Sulfuric Acid	X
Tallow	R
Tartaric Acid, 10%	R
Tatraline	R
Thionyl Chloride	X
Trichloroethylene	X
Urea In Water Solution, 20-87%	R
Zinc Chloride, 10%	X

R = Resistant with little to no chemical attack.

X = Not resistant due to moderate to severe chemical attack.

All statements, data, and information contained herein are believed to be accurate and reliable but are presented without guarantee, warranty, or responsibility of any kind, expressed or implied. You expressly understand and agree that Salco Products assumes NO obligation or liability for the statements, data, and information given. Further, you expressly understand and agree that all results which may be obtained from any use of this document are to be accepted by you at your risk alone. Salco Products hereby **DISCLAIMS ALL** liability for any use of this document.

You must evaluate and determine whether a material is suitable for your intended application. We recommend that you perform tests to determine the propriety of a material for your particular purpose prior to use.

In NO case shall anything contained in this document be considered a part of our terms and conditions of sale.

Statements or suggestions concerning the possible use of any material are made **WITHOUT** representation of warranty that any such use is free of patent infringement. We do **NOT** recommend that any patent be infringed. The user should **NOT** assume that all safety measures are indicated or that other measures may not be required.

Revised 5/14/07